

## DEUREX® A 26

### TECHNICAL INFORMATION

**Chemical description:** Erucamide wax

**Application:**

- Plastics industry (e.g. PVC, PE and PP)
- Rubber industry
- Paper Industry
- Metal processing
- Printing inks

**Properties:**

- Good antiblocking
- Excellent slip
- Defoamer for the production of paper
- Lubricant

**Technical Data:** Colour: Light yellow  
Consistencies: **DEUREX A 26 P** = Powder

	Minimum	Maximum	Method
Drop point*:	81 °C	89 °C	LV 12 (DGF M-III 3)
Acid value*:		1 mg KOH/g	DIN EN ISO 2114
Viscosity (140 °C):	7 mPas	12 mPas	LV 2 (DIN EN ISO3104)
Penetration:	2.0 mm*10 <sup>-1</sup>	5.0 mm*10 <sup>-1</sup>	LV 4 (DIN 51579)
Density (23 °C):	0.87 g/cm <sup>3</sup>	0.88 g/cm <sup>3</sup>	LV 3 (DIN EN ISO 1183)

\* Part of certificate of analysis

**Approvals:** DEUREX A 26 is approved for use in the production of consumer good used for food contact.

EU: Regulation (EU) 10/2011 dated 14. January 2011 – Ref.-No.:52720

FRG: BfR recommendation

USA: FDA 21 CFR §§ 175.10, 175.300, 176.180, 177.1210, 177.3860, 179.43

Approvals with regard to limitations and migration values in the end use application

**Safety:** The product is no dangerous preparation according to Directive 1999/45/EC. It is not subject to labelling according to EC Directive 67/548/EEC and Regulation (EC) 1272/2008.

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.

® - registered trademark by DEUREX