

## DEUREX® A 28

### TECHNICAL INFORMATION

**Chemical description:** Stearamide wax

**Application:**

- Plastics industry
- Rubber industry
- Metal processing

**Properties:**

- Lubricant
- Release agent
- Anti blocking
- Slip

**Technical Data:** Colour: White  
Consistencies: **DEUREX A 28 P** = Powder

	Minimum	Maximum	Method
Drop point*:	101 °C	111 °C	LV 12 (DGF M-III 3)
Acid value*:		5 mg KOH/g	DIN EN ISO 2114
Viscosity (140 °C):	7 mPas	12 mPas	LV 2 (DIN EN ISO3104)
Penetration:	2.0 mm*10 <sup>-1</sup>	8.0 mm*10 <sup>-1</sup>	LV 4 (DIN 51579)
Density (23 °C):	0.90 g/cm <sup>3</sup>	0.91 g/cm <sup>3</sup>	LV 3 (DIN EN ISO 1183)

\* Part of certificate of analysis

**Approvals:** DEUREX A 28 is approved for use in the production of consumer good used for food contact.

EU: Regulation (EU) 10/2011 dated 14. January 2011 – Ref.-No.:88960  
USA: FDA 21 CFR §§ 175.105, 175.300, 177.1210, 178.3910, 179.45, 181.28  
Approvals with regard to limitations and migration values in the end use application

**Safety:** The product is no dangerous preparation according to Directive 1999/45/EC. It is not subject to labelling according to EC Directive 67/548/EEC and Regulation (EC) 1272/2008.