

## DEUREX® E 0908 W

### TECHNICAL INFORMATION

<b>Chemical description:</b>	Water-based dispersion based on polyethylene wax <b>DEUREX® E 09</b>		
<b>Applications:</b>	Water-based coatings and water-based printing inks		
<b>Properties:</b>	Improved slip, abrasion and anti-blocking		
<b>Solid content:</b>	Polyethylene wax		
<b>Solvent:</b>	Purified water		
<b>Technical data:</b>	Colour:	White opaque	
	Delivery form:	Liquid	
	Packaging:	IBC 950 kg, drum 200 kg, canister 10 kg	

	Minimum	Maximum	Method
Drop point (wax)*:	110 °C	120 °C	LV 12 DGF M-III 3
Solid content*:	44 %	46 %	LV 6
Particle size*:		98 % < 8 µm	LV 09
Typical value:		50 % ~ 3 µm	
Emulsifier system:	non-ionic		
pH value:	6.5	8.5	LV 10 DIN ISO 976

\* part of certificate of analysis

<b>Processing:</b>	<ul style="list-style-type: none"> <li>- Stir well before usage</li> <li>- Consume quickly after opening</li> </ul>
<b>Storage, shelf life:</b>	<ul style="list-style-type: none"> <li>- Store at temperatures between +5 °C and +28 °C</li> <li>- Avoid frost</li> <li>- Shelf life 6 months in closed original container</li> </ul>
<b>Alternative delivery forms:</b>	<p><b>DEUREX® E 09 K</b> – Fine granules  <b>DEUREX® E 09 A</b> – Finest powder, 98 % &lt; 150 µm  <b>DEUREX® E 0920 M</b> – Micronized powder, 98 % &lt; 20 µm</p>

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.  
 ® - registered trademark by DEUREX