

## DEUREX® T 17

### TECHNICAL INFORMATION

- Chemical description:** Fischer Tropisch wax (Congealing point 70 °C)
- Applications:**
- Hot melts
- Adjustment of open time
  - Improved Adhesion
  - No stringing
- PVC
- Internal and external lubricant
- Rubber
- Protection against sun light and ozone
- Raw material for Emulsions
- Production of care products, paints and coatings
- Benefits:**
- Crystalline wax with very narrow C-chain distribution
  - Very fast solidification point at 70 °C

**Technical data:**

Colour: White  
Delivery forms: **DEUREX T 17 G** = Granules

	Minimum	Maximum	Method
Drop point*:	68 °C	78 °C	LV 12 (DGF M-III 3)
Acid value:		0 mgKOH/g	DIN EN ISO 2114
Viscosity (140 °C)*:		20 mPas	LV 2 (DIN EN ISO3104)
Penetration:	8 mm*10 <sup>-1</sup>	15 mm*10 <sup>-1</sup>	LV 4 (DIN 51579)
Density (23 °C):	0.85 g/cm <sup>3</sup>	0.90 g/cm <sup>3</sup>	LV 3 (DIN EN ISO 1183)

\* Part of certificate of analysis

- Approvals:**
- DEUREX® T 17 is approved for the production of commodities intended to come into contact with food.
- EU: Regulation (EU) 10/2011 dated 14. January
- FRG: BfR recommendation XXV
- USA: FDA 21 CFR §§ 175.105, 175.250, 175.300, 175.320, 176.170, 176.180, 177.1200, 177.1390
- (Approvals with regard to limitations and migration values in the final application)

- Safety:**
- The product is no dangerous preparation according to Directive 1999/45/EC. It is not subject to labelling according to EC Directives 67/548/EEC and Regulation (EC) 1272/2008.