

## DEUREX® T 19 G

### TECHNICAL INFORMATION

**Chemical description:**

Fischer Tropsch wax

**Applications:**

Hot melts

- Adjustment of open time
- Improved Adhesion
- No stringing

PVC

- Internal and external lubricant

Rubber

- Protection against sun light and ozone

Raw material for Emulsions

- Production of care products, paints and coatings

Raw material to produce micronized waxes

- Paints and coatings
- Increased scratch resistance and slip

**Benefits:**

- Crystalline wax with very narrow C-chain distribution
- Very fast solidification point at 80 °C

**Technical data:**

Colour: White  
Delivery forms: **DEUREX® T 19 G** = Granules

	Minimum	Maximum	Method
Drop point*:	94 °C	106 °C	ASTM D 3954
Acid value:		0 mgKOH/g	ASTM D 1386
Viscosity (140 °C)*:		15 mPas	ISO 3219
Penetration:		5 mm*10 <sup>-1</sup>	ASTM D 1321
Density (23 °C):	0.89 g/cm³	0.91 g/cm³	ISO 1183

\* Part of certificate of analysis

**Approvals:**

Food contact approvals

**Alternative products:**

See <https://www.deurex.com/productsearch/DEUREX-T-19-G/>