

DEUREX® T 39 B

TECHNICAL INFORMATION

Chemical description:

Fischer-Tropsch wax

Bitumen (Stone Mastic Asphalt, SMA and Asphalt Concrete, AC)

Road construction (bitumen modifier, road marking)

- Very good heat resistance
- Precise reduction of viscosity
- Reduction of the processing temperature (warm mix)
- Easier workability
- Improvement of process reliability (reduction of vapors and aerosols)
- Suitable for recycling of bitumen
- Improvement of the durability of bitumen (aging, resilience)
- Reduction of heating energy (costs)
- Excellent price / performance ratio
- Improvement of work safety (dust-free and lower temperatures)
- Can be mixed homogeneously and compatible with all bitumen systems
- Polymer stabilized Bitumen

Benefits:

- Very fast solidification point at 100 °C
- Dispersing agent
- Technical equivalent to DEUREX® T 39 K

Technical data:

Colour: Off-white / Yellowish
Delivery forms: **DEUREX® T 39 B** = Granules



	Minimum	Maximum	Method
Drop point*:	110 °C	118 °C	LV 12 (DGF M-III 3)
Acid value:		0 mg KOH/g	DIN EN ISO 2114
Viscosity (140 °C)*:		20 mPas	LV 2 (DIN EN ISO3104)
Penetration (25 °C):		5 mm*10 ⁻¹	LV 4 (DIN 51579)
Density (23 °C):	0.94 g/cm ³	0.95 g/cm ³	LV 3 (DIN EN ISO 1183)

* Part of certificate of analysis

Alternative delivery forms:

DEUREX® T 39 K – Granules (Off-white)

Alternative products:

DEUREX® E 11 B – Polyethylen wax granules
DEUREX® A 20 K – EBS wax granules

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.
® - registered trademark by DEUREX