

## DEUREX® T 16 G

### TECHNICAL INFORMATION

- Chemical description:** Fischer Tropisch wax (Congealing point 60 °C)
- Applications:**
- Hot melts
    - Adjustment of open time
    - Improved Adhesion
    - No stringing
  - PVC
    - Internal and external lubricant
  - Rubber
    - Protection against sun light and ozone
  - Raw material for Emulsions
    - Production of care products, paints and coatings
- Benefits:**
- Crystalline wax with very narrow C-chain distribution
  - Very fast solidification point at 60 °C

**Technical data:**

Colour: White  
Delivery forms: **DEUREX T 16 G** = Granules

	Minimum	Maximum	Method
Congealing point*:	55 °C	65 °C	LV 12 (DGF M-III 3)
Acid value:		0 mgKOH/g	DIN EN ISO 2114
Viscosity (140 °C):		5 mPas	LV 2 (DIN EN ISO3104)
Penetration:		25 mm*10 <sup>-1</sup>	LV 4 (DIN 51579)
Density (23 °C):	0.85 g/cm <sup>3</sup>	0.90 g/cm <sup>3</sup>	LV 3 (DIN EN ISO 1183)

\* Part of certificate of analysis

**Safety:**

The product is no dangerous preparation according to Directive 1999/45/EC. It is not subject to labelling according to EC Directives 67/548/EEC and Regulation (EC) 1272/2008.