

## **DEUREX® B 66 A**

**TECHNICAL INFORMATION** 

Chemical description: Micronized EBS wax, coated with Benzoin based on

50% BENZOIN Micro and 50% DEUREX® A 2015 M (EBS)

Applications: Degassing agent for powder coatings

Benefits: - 16 times larger surface than Benzoin, therefore better degassing

- "B 66 A" replaces two raw materials, the Benzoin and EBS waxes in

powder coating formulations

**Properties:** - Effective and rapid degassing

- No yellowing (< 230 °C)

- Good printability of the powder coating remains

- Good adhesion of labels remains

Technical data: Colour: Off-white

Delivery forms: **DEUREX® B 66 A** = Finest powder, 98% < 150 μm

	Minimum	Maximum	Method
Drop point*:	133 °C	139 °C	ASTM D4591
Density (23 °C):	1.25 g/cm <sup>3</sup>	1.35 g/cm <sup>3</sup>	LV 3 (DIN EN ISO 1183)
Shelf life:	12 months (In closed, original containers in compliance with storage conditions)		

<sup>\*</sup> Part of certificate of analysis

Safety: This product is not classified as dangerous preparation according to Directive

1999/45/EC. It is not subject to labelling according to EC Directive 67/548/EEC and

Regulation (EC) 1272/2008.

Alternative products: DEUREX® A 2015 M – Micronized EBS wax, 98% < 15 μm

**DEUREX® X 2010 M –** Renewable vegetable EBS wax, 98% < 10 μm

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.

⑤ - registered trademark by DEUREX