

## DEUREX® B 66 A

### TECHNICAL INFORMATION

**Chemical description:** Micronized EBS wax, coated with benzoin  
Based on 50% benzoin and 50% DEUREX® A 2015 M (EBS)

**Applications:** Degassing agent for powder coatings

**Benefits:**

- 16 times larger surface than benzoin, therefore better degassing
- Replaces the use of benzoin and the use of micronized EBS waxes
- 2 in 1 product, reduces warehousing and handling
- AIR CLASSIFICATION PROCESS with fineness < 150 µm
- "B 66 A" replaces two raw materials, the benzoin and EBS waxes in powder coating formulations

**Properties:**

- Effective and rapid degassing
- No yellowing (< 230 °C)
- Good printability of the powder coating remains
- Good adhesion of labels remains

**Technical data:** Colour: Off-white  
Delivery forms: **DEUREX® B 66 A** = Finest powder, 98% < 150 µm

	Minimum	Maximum	Method
Drop point*:	133 °C	139 °C	ASTM D4591
Density (23 °C):	1.25 g/cm³	1.35 g/cm³	LV 3 (DIN EN ISO 1183)
Shelf life:	12 months (In closed, original containers in compliance with storage conditions)		

\* Part of certificate of analysis

**Safety:** This product is not classified as dangerous preparation according to Directive 1999/45/EC. It is not subject to labelling according to EC Directive 67/548/EEC and Regulation (EC) 1272/2008.

**Alternative products:** **DEUREX® BENZOIN** – Pure Benzoin  
**DEUREX® A 2015 M** – Micronized EBS wax, 98% < 15 µm  
**DEUREX® X 2010 M** – Renewable vegetable EBS wax, 98% < 10 µm