

## DEUREX A 2625 M

### TECHNICAL INFORMATION

**Chemical description:** Micronized vegetable erucamide wax

**Applications:** Paints and coatings

- Thermosensitive paper

Printing inks

- Gravure printing, overprint varnishes, screen printing inks
- Flexo-, web-, sheet-fed-, offset- and coldset inks

Paper industry, plastics industry, metal industry

Additive for ceramics

**Properties:**

- Very good anti-blocking and slip
- Lubricant
- Good recoatability and wet printing properties
- Defoamer for paper production
- Surface lubricant for the metal production

**Benefits:**

- Guaranteed maximum particle size; constant and narrow particle size distribution

**Technical data:**

Colour: White

Delivery form: **DEUREX A 2625 M** = Micronized powder

	Minimum	Maximum	Method
Particle size*:		98 % < 25 µm	ISO 13320
Typical value:		50 % ~ 7 µm	
Drop point*:	81 °C	89 °C	ASTM D 3954
Acid value*:		1 mg KOH/g	ASTM D 1386
Penetration:		45 mm*10 <sup>-1</sup>	ASTM D 1321
Density (23 °C):	0.87 g/cm <sup>3</sup>	0.88 g/cm <sup>3</sup>	ISO 1183

\* Part of certificate of analysis

**Approvals:** Food contact approvals

**Alternative products:** See <https://www.deurex.com/productsearch/DEUREX-A-2625-M/>

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.