

DEUREX® T 18

TECHNICAL INFORMATION

- Chemical description:** Microcrystalline wax
- Applications:**
- PVC
- Lubricant, packaging vegetables, bread, meat, sweets
- Rubbe
- Protection against sunlight and ozone
 - Excellent migration behaviour
- Cable
- Resistance against oil
 - Resistance against cold
 - Rub resistance
- Hot melts
- Adjustment of open time
 - Improved adhesion, no stringing

Technical data:

Colour: Off-white
Delivery forms: **DEUREX® T 18 K** = Fine granules

	Minimum	Maximum	Method
Drop point*:	80 °C	85 °C	LV 12 (DGF M-III 3)
Acid value:		0 mgKOH/g	DIN EN ISO 2114
Viscosity (140 °C)*:		20 mPas	LV 2 (DIN EN ISO3104)
Penetration:	10 mm*10 ⁻¹	22 mm*10 ⁻¹	LV 4 (DIN 51579)
Density (23 °C):	0.75 g/cm ³	0.85 g/cm ³	LV 3 (DIN EN ISO 1183)

* Part of certificate of analysis

Approvals:

DEUREX® T 18 is approved for the production of commodities intended to come into contact with food.
EU: Regulation (EU) 10/2011
FRG: BfR recommendation XXV
USA: FDA 21 CFR §§ 172.886, 175.105, 175.300, 175.320, 176.170, 176.180, 176.200, 176.210, 177.1200, 177.1210, 177.1350, 177.1390
(Approvals with regard to limitations and migration values in the final application)

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.
® - registered trademark by DEUREX