

## DEUREX T 17 G

### TECHNICAL INFORMATION

**Chemical description:** Fischer Tropsch wax (Congealing point 70 °C)

**Applications:** Hot melts

- Adjustment of open time
- Improved Adhesion
- No stringing

PVC

- Internal and external lubricant

Rubber

- Protection against sun light and ozone

Raw material for Emulsions

- Production of care products, paints and coatings

**Benefits:**

- Crystalline wax with very narrow C-chain distribution
- Very fast solidification point at 70 °C

**Technical data:**

Colour: White

Delivery forms: **DEUREX T 17 G** = Granules

	Minimum	Maximum	Method
Drop point*:	75 °C	85 °C	ASTM D 3954
Acid value:		0 mgKOH/g	ASTM D 1386
Viscosity (140 °C):		10 mPas	ISO 3219
Penetration:	10 mm*10 <sup>-1</sup>	15 mm*10 <sup>-1</sup>	ASTM D 1321
Density (23 °C):	0.85 g/cm <sup>3</sup>	0.90 g/cm <sup>3</sup>	ISO 1183

\* Part of certificate of analysis

**Approvals:** Food contact approvals

**Alternative products:** See <https://www.deurex.com/productsearch/DEUREX-T-17-G/>

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.