

DEUREX® T 17 G

TECHNICAL INFORMATION

- Chemical description:** Fischer Tropisch wax (Congealing point 70 °C)
- Applications:**
- Hot melts
 - Adjustment of open time
 - Improved Adhesion
 - No stringing
 - PVC
 - Internal and external lubricant
 - Rubber
 - Protection against sun light and ozone
 - Raw material for Emulsions
 - Production of care products, paints and coatings
- Benefits:**
- Crystalline wax with very narrow C-chain distribution
 - Very fast solidification point at 70 °C

Technical data:

Colour: White
Delivery forms: **DEUREX T 17 G** = Granules

	Minimum	Maximum	Method
Drop point*:	68 °C	78 °C	LV 12 (DGF M-III 3)
Acid value:		0 mgKOH/g	DIN EN ISO 2114
Viscosity (140 °C):		20 mPas	LV 2 (DIN EN ISO3104)
Penetration*:	8 mm*10 ⁻¹	15 mm*10 ⁻¹	LV 4 (DIN 51579)
Density (23 °C):	0.85 g/cm ³	0.90 g/cm ³	LV 3 (DIN EN ISO 1183)

* Part of certificate of analysis

- Approvals:**
- DEUREX® T 17 G is approved for the production of commodities intended to come into contact with food.
- EU: Regulation (EU) 10/2011 dated 14. January
FRG: BfR recommendation XXV
USA: FDA 21 CFR §§ 175.105, 175.250, 175.300, 175.320, 176.170, 176.180, 177.1200, 177.1390
(Approvals with regard to limitations and migration values in the final application)

- Safety:**
- The product is no dangerous preparation according to Directive 1999/45/EC. It is not subject to labelling according to EC Directives 67/548/EEC and Regulation (EC) 1272/2008.