

DEUREX® TO 80 G

TECHNICAL INFORMATION

- Chemical description:** Oxidized linear structured Fischer-Tropsch-wax
- Applications:** PVC and other plastics
 - Can be used in all U-PVC and P-PVC applications but also in C-PVC
- Properties:** Partially internal and external wax, highly effective which
 - Accelerate fusion,
 - Decreases torque and increases pressure
 - Synergistic effect in combination with non-polar PE waxes by reduction of melt viscosity
 - Useful in combination with tin stabilisers
- Typical dosages:** Depending on the rheological requirements
 - Up to 0.5 phr in combination with calcium-zinc
 - Up to 1.0 phr in combination with tin

Technical data:

Colour: Off-white
 Delivery form: **DEUREX TO 80 G** = Granules

	Minimum	Maximum	Method
Congealing point*:	97 °C	103 °C	LV 12 (DGF M-III 3)
Acid value*:	2 mgKOH/g	4 mgKOH/g	DIN EN ISO 2114
Viscosity (140 °C):		20 mPas	LV 2 (DIN EN ISO3104)
Penetration:		1.0 mm*10 ⁻¹	LV 4 (DIN 51579)
Density (23 °C):	0.94 g/cm ³	0.95 g/cm ³	LV 3 (DIN EN ISO 1183)

* Part of certificate of analysis

Additional lubricants:

DEUREX® E 11 K – Homopolymered PE-Wachs
DEUREX® EO 40 K – Oxidized LDPE wax
DEUREX® EO 44 K – Oxidized HDPE wax
DEUREX® T 39 K – Fischer Tropsch wax

Alternative delivery form:

DEUREX® T 3901 W – Fischer-Tropsch-wax emulsion

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.
 ® - registered trademark by DEUREX