

## DEUREX® H 9215 M

### TECHNICAL INFORMATION

<b>Chemical description:</b>	Micronized hybrid wax based on Polyethylene wax and Amide wax		
<b>Production process:</b>	Homogeneously melted wax hybrid, micronized by DEUREX® air classification		
<b>Benefits:</b>	<p>Hybrid waxes offer a variety of wax properties:</p> <ul style="list-style-type: none"> <li>- Contains short-chained polyethylene waxes to optimize adhesion and flexibility on the surface of the end product as well as UV resistance</li> <li>- Contains high-melting polyolefin waxes to increase the temperature resistance and hydrophilicity of the surface</li> <li>- Contains high-melting amide waxes to increase the temperature resistance but above all to improve the anti-blocking and free flowing properties, the degassing as well as to avoid the formation of agglomerates</li> </ul>		
<b>Applications:</b>	<p><u>Liquid coatings</u></p> <ul style="list-style-type: none"> <li>- Very good scratch resistance</li> <li>- Lowers the coefficient of friction (slip)</li> <li>- Improves abrasion resistance and minimizes metal markings</li> <li>- Soft touch and anti-blocking properties</li> </ul> <p><u>Printing inks</u></p> <ul style="list-style-type: none"> <li>- Slip and rub resistance</li> <li>- Anti-blocking properties</li> </ul>		
<b>Properties:</b>	<ul style="list-style-type: none"> <li>- Excellent rub resistance after a short drying time</li> <li>- Gloss-reducing properties in all coatings</li> </ul>		
<b>Processing:</b>	<ul style="list-style-type: none"> <li>- Economically beneficial due to the usage of less energy and lower temperatures in the production process</li> <li>- Reduction of manufacturing costs by quickly and effectively processing</li> </ul>		
<b>Technical data:</b>	Colour:	White	
	Delivery form:	DEUREX® H 9215 M = Micronized powder	
		Minimum	Maximum
	Particle size*:		98 % < 15 µm
	Typical value:		50 % ~ 6 µm
	Drop point*	130 °C	140 °C
	Acid value:		5 mgKOH/g
	Penetration:		5 mm*10 <sup>-1</sup>
	Density (23 °C):	0.97 g/cm <sup>3</sup>	0.99 g/cm <sup>3</sup>
			Method
			LV 5 (DIN ISO 13320)
			LV 12 (DGF M-III 3)
			DIN EN ISO 2114
			LV 4 (DIN 51579)
			LV 3 (DIN ISO 1183)
* Part of certificate of analysis			
<b>Alternative delivery forms:</b>	<p>DEUREX® H 92 G – Granules</p> <p>DEUREX® H 92 A – Finest powder, 98% &lt; 150 µm</p> <p>DEUREX® H 9220 M – Micronized powder, 98% &lt; 20 µm</p> <p>DEUREX® H 9208 W – Micronized powder, 98% &lt; 8 µm</p>		

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.

® - registered trademark by DEUREX