

DEUREX H 9620 M

TECHNICAL INFORMATION

Chemical description:	Micronized hybrid wax, based on Polypropylene, Polyethylene, Amide and Fischer-Tropsch wax																																
Benefits:	<p>Hybrid waxes offer a variety of properties:</p> <ul style="list-style-type: none"> - Contains short-chained polyethylene waxes to optimize adhesion and flexibility on the surface of the end product and UV resistance - Contains high-melting polypropylene waxes to increase the temperature resistance, UV and chemical resistance - Contains high-melting amide waxes to increase the temperature resistance but above all to improve the anti-blocking and free flowing properties, the degassing and to avoid the formation of agglomerates - Contains long-chained hard paraffins (FT waxes) to increase scratch, abrasion and heat resistance 																																
Applications:	<p><u>Liquid coatings</u></p> <ul style="list-style-type: none"> - Very good scratch resistance - Lowers the coefficient of friction (slip) - Improves abrasion resistance and minimizes metal markings - Soft touch and anti-blocking properties <p><u>Printing inks</u></p> <ul style="list-style-type: none"> - Slip and rub resistance, anti-blocking properties <p><u>Powder coatings</u></p> <ul style="list-style-type: none"> - Improves flowability of the powder - Provides slip and scratch resistance 																																
Properties:	<ul style="list-style-type: none"> - Excellent rub resistance after a short drying time 																																
Processing:	<ul style="list-style-type: none"> - Economically beneficial due to the usage of less energy and lower temperatures in the production process - Reduction of manufacturing costs by quickly and effectively processing 																																
Technical data:	<table border="0"> <tr> <td>Colour:</td> <td colspan="3">White</td> </tr> <tr> <td>Delivery form:</td> <td colspan="3">DEUREX H 9620 M = Micronized powder</td> </tr> <tr> <td></td> <td>Minimum</td> <td>Maximum</td> <td>Method</td> </tr> <tr> <td>Particle size*:</td> <td></td> <td>98 % < 20 µm</td> <td>ISO 13320</td> </tr> <tr> <td>Typical value:</td> <td></td> <td>50 % ~ 6 µm</td> <td></td> </tr> <tr> <td>Drop point*</td> <td>143 °C</td> <td>153 °C</td> <td>ASTM D 3954</td> </tr> <tr> <td>Penetration:</td> <td></td> <td>3 mm*10⁻¹</td> <td>ASTM D 1321</td> </tr> <tr> <td>Density (23 °C):</td> <td>0.97 g/cm³</td> <td>0.99 g/cm³</td> <td>ISO 1183</td> </tr> </table> <p>* Part of certificate of analysis</p>	Colour:	White			Delivery form:	DEUREX H 9620 M = Micronized powder				Minimum	Maximum	Method	Particle size*:		98 % < 20 µm	ISO 13320	Typical value:		50 % ~ 6 µm		Drop point*	143 °C	153 °C	ASTM D 3954	Penetration:		3 mm*10 ⁻¹	ASTM D 1321	Density (23 °C):	0.97 g/cm ³	0.99 g/cm ³	ISO 1183
Colour:	White																																
Delivery form:	DEUREX H 9620 M = Micronized powder																																
	Minimum	Maximum	Method																														
Particle size*:		98 % < 20 µm	ISO 13320																														
Typical value:		50 % ~ 6 µm																															
Drop point*	143 °C	153 °C	ASTM D 3954																														
Penetration:		3 mm*10 ⁻¹	ASTM D 1321																														
Density (23 °C):	0.97 g/cm ³	0.99 g/cm ³	ISO 1183																														
Approvals:	Food contact approvals																																
Alternative products:	See https://www.deurex.com/productsearch/DEUREX-H-9620-M/																																

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.