

DEUREX® H 9620 M

TECHNICAL INFORMATION

- Chemical description:** Micronized hybrid wax, based on Polypropylene, Polyethylene, Amide and Fischer-Tropsch wax
- Production process:** Homogeneously melted wax hybrid, micronized by DEUREX® air classification
- Benefits:** Hybrid waxes offer a variety of properties:
- Contains short-chained polyethylene waxes to optimize adhesion and flexibility on the surface of the end product and UV resistance
 - Contains high-melting polypropylene waxes to increase the temperature resistance, UV and chemical resistance
 - Contains high-melting amide waxes to increase the temperature resistance but above all to improve the anti-blocking and free flowing properties, the degassing and to avoid the formation of agglomerates
 - Contains long-chained hard paraffins (FT waxes) to increase scratch, abrasion and heat resistance
- Applications:**
- Liquid coatings
- Very good scratch resistance
 - Lowers the coefficient of friction (slip)
 - Improves abrasion resistance and minimizes metal markings
 - Soft touch and anti-blocking properties
- Printing inks
- Slip and rub resistance, anti-blocking properties
- Powder coatings
- Improves flowability of the powder
 - Provides slip and scratch resistance
- Properties:**
- Excellent rub resistance after a short drying time
 - Less agglomerates in the product
- Processing:**
- Economically beneficial due to the usage of less energy and lower temperatures in the production process
 - Reduction of manufacturing costs by quickly and effectively processing

Technical data:

Colour: White
Delivery form: **DEUREX® H 9620 M** = Micronized powder

	Minimum	Maximum	Method
Particle size*:		98 % < 20 µm	LV 5 (DIN ISO 13320)
Typical value:		50 % ~ 6 µm	
Drop point*	143 °C	153 °C	LV 12 (DGF M-III 3)
Acid value:		2 mgKOH/g	DIN EN ISO 2114
Penetration:		3 mm*10 ⁻¹	LV 4 (DIN 51579)
Density (23 °C):	0.97 g/cm³	0.99 g/cm³	LV 3 (DIN ISO 1183)

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.
® - registered trademark by DEUREX

* Part of certificate of analysis

Alternative products:

DEUREX® H 9215 M – Micronized Hybrid wax powder, 98% < 15 µm

DEUREX® H 9415 M – Micronized FT & EBS wax powder, 98% < 15 µm

DEUREX® H 9515 M – Micronized FT, EBS & PE wax powder, 98% < 15 µm

DEUREX® P 3820 M – Micronized Polypropylene wax powder, 98% < 20 µm

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.
® - registered trademark by DEUREX