

## DEUREX E 0915 M

### TECHNICAL INFORMATION

**Chemical description:** Micronized Polyethylene wax

**Applications:**

- Paints and coatings
- Industrial- and wood coatings
  - Can-, coil-, automotive-, furniture and parquet coatings

Printing inks

- Gravure printing, overprint varnishes, screen printing inks
- Flexo-, web-fed-, sheetfed offset-, and coldset inks

**Properties:**

- High abrasion and scratch resistance
- Very good dispersion properties
- Very good anti-blocking and slip
- Increase in surface gloss

**Technical data:**

Colour: White  
Delivery form: **DEUREX E 0915 M** = Micronized powder

	Minimum	Maximum	Method
Particle size*:		98 % < 15 µm	ISO 13320
Typical value:		50 % ~ 6 µm	
Drop point*:	104 °C	118 °C	ASTM D 3954
Penetration:	3 mm*10 <sup>-1</sup>	6 mm*10 <sup>-1</sup>	ASTM D 1321
Density (23 °C):	0.94 g/cm <sup>3</sup>	0.96 g/cm <sup>3</sup>	ISO 1183

\* Part of certificate of analysis

**Approvals:**

Food contact approvals

**Alternative products:**

See <https://www.deurex.com/productsearch/DEUREX-E-0915-M/>

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.