

DEUREX A 24 K

TECHNICAL INFORMATION

Chemical description:	Behenamide wax		
Application:	<u>Plastics industry</u> (e.g. PVC, PE and PP) - Improve clarity of PE and PP film		
	<u>Paper Industry</u> - Defoamer for the production of paper		
	<u>Metal processing</u> - Surface lubricant for metal production		
	<u>Printing inks</u> - Improves the dye distribution - Good overprintability and wet printing properties		
Properties:	- Excellent Anti-blocking and slip agent - Lubricant - Release agent - Processing aid - Dust free		
Technical Data:	Colour:	White	
	Consistencies:	DEUREX A 24 K = Fine granules	
		Minimum	Maximum
	Drop point*:	110 °C	120 °C
	Acid value*:	1 mg KOH/g	
	Viscosity (140 °C)*:	3 mPas	10 mPas
	Penetration:	3.0 mm*10 ⁻¹	9.0 mm*10 ⁻¹
	Density (23 °C):	0.90 g/cm ³	0.92 g/cm ³

* Part of certificate of analysis

Approvals: Food contact approvals

Alternative products: See <https://www.deurex.com/productsearch/DEUREX-A-24-K/>

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.