

## BIOMER 128 P

### TECHNICAL INFORMATION

<b>Product Family:</b>	<b><u>BIOMER – biodegradable waxes</u></b>
<b>Product Description:</b>	Hardwax, modified, dry oxidized, branched chains
<b>Benefits:</b>	Biodegradable high melting wax to prevent the formation of micro plastics
<b>Biodegradability:</b>	Raw material is biodegradable according to the test method OECD 301 B
<b>Technical Data:</b>	Colour: White

	Typical value	Method
Drop point*:	132 – 136 °C	ASTM D 3954
Viscosity (140°C):	< 4.000 mPas	ISO 3219
Acid value:	14 – 18 mg KOH/g	ASTM D 1386
Penetration:	< 2 mm*10 <sup>-1</sup>	ASTM D 1321

### **BIOMER 128 P**

Form of delivery: Powder

*\*part of certificate of analysis*

<b>Storage, Shelf life:</b>	<b>Solid form:</b> Dry storage. Store at temperatures (+5 °C to +28 °C) Shelf life: minimum 24 months
-----------------------------	--

<b>Further Information:</b>	Application, Properties, alternative Products: <a href="https://www.deurex.com/productsearch/BIOMER-128-P/">https://www.deurex.com/productsearch/BIOMER-128-P/</a>
-----------------------------	---

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.