

DEUREX A 2520 M

TECHNICAL INFORMATION

Chemical description: Micronized vegetable Ethylen-Bis-Oleamid (EBO) wax

Application:

- Paints and coatings
- Excellent overprintability
- Metal processing
- Surface lubricant for metal production
- Printing inks
- Improves the dye distribution
 - Good overprintability and wet printing properties
- Rubber industry
- Mold release agents
 - Increases the abrasion resistance

Properties:

- Paper industry
- Excellent overprintability of colours (suitable for corona-untreated films)
 - Excellent slip
 - Very good Anti-blocking properties
 - Anti-sticking agent & mold release aids
 - Brighteners, smoothing agents, non-stick agents
 - Good scratch & abrasion resistance
 - Improved tape test performance
 - Dust free

Technical Data:

Colour: Light yellow
Delivery form: **DEUREX A 2520 M** = Micronized powder

	Minimum	Maximum	Method
Particle size*:		98 % < 20 µm	ISO 13320
Typical value:		50 % ~ 8 µm	
Drop point*:	110 °C	120 °C	ASTM D 3954
Acid value:	2 mg KOH/g	6 mg KOH/g	ASTM D 1386
Viscosity (140 °C):	7 mPas	12 mPas	ISO 3219
Penetration:	5.0 mm*10 ⁻¹	10.0 mm*10 ⁻¹	ASTM D 1321
Density (23 °C):	0.97 g/cm ³	0.99 g/cm ³	ISO 1183

* Part of certificate of analysis

Approvals:

Food contact approvals

Alternative products:

See <https://www.deurex.com/productsearch/DEUREX-A-2520-M/>

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.