

DEUREX K 64 TEX

TECHNICAL INFORMATION

Chemical description:	PEEK coated Wax Micronized Hardwax, coated with structuring high-performance polymer PEEK (Polyetheretherketone) (Eco coated)		
Benefits:	<ul style="list-style-type: none"> - Wax surface eco coated with PEEK - Uniform texture at low dosages - PFAS free – PTFE alternative - Extreme surface hardness - PEEK sticks to the surface of the wax 		
Applications:	<u>Paints and coatings</u> <ul style="list-style-type: none"> - Powder coatings, can coatings, furniture and parquet coatings - Automotive, industrial, painting and construction coatings - Especially for sheetfed offset inks, as well as flexographic and gravure inks - PEEK (Polyetheretherketone) is a high-performance thermoplastic used in very demanding technical applications 		
Properties:	<ul style="list-style-type: none"> - Allows a wide selection of controlled textures - High temperature resistance - Very high strength and rigidity - Very hard wax - Excellent chemical resistance - Excellent wear and abrasion resistance - Very good slip properties, high fatigue strength - Biocompatibility & radiation resistance - High dielectric strength and stable insulating properties - Low dust behaviour, free-flowing powder - Good dispersibility in water, oil and solvents 		
Technical data:	Colour:	White	
	Delivery form:	Finest powder	
		Minimum	Maximum
	Drop point _{(wax)*} :	130 °C	135 °C
	Density (23 °C) _(wax) :	0,97 g/cm ³	0,99 g/cm ³
	Typical melting point _(PEEK) :	340 °C	ISO 11357
	Typical density (23 °C) _(PEEK) :	1,30 g/cm ³	ISO 1183

*Part of certificate of analysis

Alternative products: See <https://www.deurex.com/productsearch/DEUREX-K-64-TEX/>

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.