

## DEUREX T 49 A

### TECHNICAL INFORMATION

<b>Chemical description:</b>	Fischer-Tropsch wax			
<b>Applications:</b>	<u>Paints and coatings</u> <ul style="list-style-type: none"><li>- Powder coating, industrial- and wood coatings</li><li>- Can-, coil-, automotive-, furniture and parquet coatings</li></ul> <u>Printing inks</u> <ul style="list-style-type: none"><li>- Gravure printing, overprint varnishes, screen printing inks</li><li>- Flexo-, web-fed-, sheetfed offset-, and coldset inks</li></ul>			
<b>Properties:</b>	<ul style="list-style-type: none"><li>- High melting point</li><li>- Excellent abrasion and scratch resistance</li><li>- Very good chemical and weather resistance</li><li>- Improved UV resistance</li></ul>			
<b>Technical data:</b>	Colour:	White		
	Delivery form:	Finest powder, 98 % < 150 µm		
		Minimum	Maximum	Method
	Drop point*:	111 °C	120 °C	ASTM D 3954
	Penetration:		1 mm*10 <sup>-1</sup>	ASTM D 1321
	Density (23 °C):	0.94 g/cm <sup>3</sup>	0.95 g/cm <sup>3</sup>	ISO 1183
	* Part of certificate of analysis			
<b>Approvals:</b>	Food contact approvals			
<b>Alternative products:</b>	See <a href="https://www.deurex.com/productsearch/DEUREX-T-49-A/">https://www.deurex.com/productsearch/DEUREX-T-49-A/</a>			

This data sheet is based on our current knowledge and experience. In view of the individual factors that may affect processing and application, this data does not relieve users from the responsibility of carrying out their own tests and experiments, neither do they imply any legally binding assurance of certain properties. Existing industrial/commercial protective laws have to be considered by the recipient. Updated versions of the data sheet replace all formerly existing versions.